DATA SHEET

SHELLDIE®

~AISI H11 - W.Nr. 1.2343 - X37CrMoV5-1 HOT WORK TOOL STEEL

TYPICAL APPLICATIONS

- Tooling for Aluminum Die Casting
- Aluminum and magnesium extrusion dies
- · Die inserts and forging dies
- Plastic Mold Dies
- Cores, sleeves and slides

GENERAL

Delivery Condition: Annealed to 229 BHN Max. EFVD, ESR or VAR

Non-NADCA: **SD®** NADCA Grade E: **SDQ®** ESR or VAR

ShellDie[®] is a high quality tool steel with high impact resistance. They also has good wear and heat checking resistance at high temperature.

SD[®] is a H11 modified type steel with higher molybdenum for added heat resistance over standard H11. Alloy composition is balanced in order to reduce primary carbide formation for improved fracture toughness.

SD[®] and **SDQ**[®] have an excellent combination of high strength and toughness at high temperature and can reach hardnesses typically in the 42 to 52 HRC with standard hardening procedures by most vacuum heat treating operations.

Typical Chemical Analysis - % weight

IKL S

SCHMOLZ + BICKENBACH GROUF

С	Mn	Si	Cr	Мо	V
0.36	0.55	0.50	5.15	1.85	0.35

SD[®] is forged using a special densifying process which assures optimum consolidation of centers.

SD[®] is forged on our largest presses equipped with wide dies assuring maximum deformation during forging process.

SD[®] is characterized by :

- Improved wear resistance
- Improved heat checking resistance
- Improved fracture toughness
- High temperature strength
- High impact resistance

SD[®] and **SDQ**[®] are 100% ultrasonic tested to very stringent acceptance levels.

SDQ[®] can be supplied pre-certified to NADCA standard #207 Grade E on request.

[®]Finkl Steel Trademark

DATA SHEET HOT WORK TOOL STEEL

SHELLDIE®

HEAT TREATMENT

ANNEALING

Temperature: 1500-1550°F (815-845°C) Rate of cooling: 25°F (15°C) max per hour Typical annealed hardness: 229 BHN Max.

Key parameter of the NADCA recommended procedure for hardening dies for die casting service are:

HARDENING

Rate of heating: slow Preheat Temperature: 1200-1300°F (650-705°C) Hardening Temperature: 1810-1885°F (985-1030°C) Time at temperature: 30-45 minutes Quenching to 300°F (150°C)

TEMPERING

Tempering Temperature: 1050°F (565°C) minimum

STRESS RELIEVING

Temperature: 50-100°F (30-55°C) below final tempering temperature and slow cool to 875°F (470°C), then air cool.

Note: Provided technical data and information in this data sheet are typical values. Normal variations in chemistry, size and conditions of heat treatment may cause deviations from these values. We suggest that information be verified at time of enquiry or order. For additional data or metallurgical assistance, please contact us.

SIZE SD®

(Finished / approx.)

Max weight	16330 kg	36000 lbs
Max section	0.90 m ²	1400 sq in
Max width	1 270 mm	5 0 ″
Max thickness	760 mm	30″





FINKL STEEL offers select customers the opportunity to participate in the Finkl Partner Program, a Webbased system that allow for:

- Online quoting and ordering
- Real-time order tracking
- Customized report generation

Contact your Finkl representative to learn more about online business services.

Finkl Steel—Chicago

1355 E. 93rd Street Chicago, IL 60619

773.975.2510 TOLL-FREE: 800.621.1460 FAX: 773.348.5347 www.finkl.com

Finkl Steel—Sorel

100 McCarthy Street St-Joseph-de-Sorel Quebec, Canada J3R 3M8

450.746.4122 TOLL-FREE: 800.363.9484 www.sorelforge.com

Finkl Steel—Composite

2300 W. Jefferson Avenue Detroit, MI 48216

FINKL STEEL

313.496.8599 www.compforge.com